... d PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6: (11) International Publication Number: WO 98/07897 C23F 17/00, 15/00 // B24B 1/00, C23C A1 26 February 1998 (26.02.98) (43) International Publication Date: 22/63, C25D 3/38, 3/40, B63H 1/14, 1/28 (81) Designated States: AL, AU, BB, BG, BR, BY, CA, CN, CZ, (21) International Application Number: PCT/AU97/00543 EE, GE, HU, IL, IS, JP, KP, KR, LK, LR, LS, LT, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, RO, SG, SI, 21 August 1997 (21.08.97) (22) International Filing Date: SK, TR, TT, UA, US, UZ, VN, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, (30) Priority Data: DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, ΑU 22 August 1996 (22.08.96) PO 1806 MR, NE, SN, TD, TG). (71)(72) Applicant and Inventor: KEMPIN, Ronald [AU/AU]; 3 Rodgers Place, Bull Creek, W.A. 6149 (AU). **Published** With international search report.

(54) Title: PREVENTION OF MARINE ENCRUSTATION ON BRONZE PROPELLERS

(57) Abstract

From the time that they are immersed into a marine environment, bronze propellers are prone to attack by marine organisms, such as barnacles, coral and algae, which attach themselves to the bronze metallic surface, creating lumps on the propeller, which adversely affect its balance and cause impedance and vibration of the propeller and its boat in the water. Ant-fouling paints are either too toxic for the marine environment of lack smoothness on the surface. These problems have been overcome by a combination of known steps, namely, polishing the propeller to prepare it for electroplating, cleansing to remove all traces of dirt and grease, electroplating with copper to a depth of at least 0.005" or 0.15 mm, followed by spraying with a standard solution (5 %) of sodium hypochlorite and sodium chloride in a suitable container to form a firmly adhering conversion coating of basic cupric chloride and then sealing for at least twenty-four hours. The preferred procedure for polishing is 60# grit size at 3500 sfm for roughing, followed by 180# grit size at 5500 sfm for finishing using grease as a polishing aid. Electroplating with copper to the minimum depth provides a smoothing effect ranging from 70 to 90 per cent. The container in which the hypochlorite spraying is carried out is preferably kept sealed until just before fitting and launching. A life expectancy of five (5) years can be anticipated with minimal maintenance every time the vessel is slipped.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL Albania AM Armenia AT Austria AU Austria AZ Azerbaijan BA Bosnia and Hern BB Barbados BE Belgium BF Burkina Faso BG Bulgaria BJ Benin BR Brazil BY Belarus CA Canada CF Central African I CG Congo CH Switzerland CI Côte d'Ivoire CM Cameroon CN China CU Cuba CZ Czech Republic DE Germany DK Denmark EE Estonia	GH GN GR HU IB IL IS	Spain Finland France Gabon United Kingdom Georgia Ghana Guinea Greece Hungary Ireland Israel Iceland Italy Japan Kenya Kyrgyzstan Democratic People's Republic of Korea Republic of Korea Republic of Korea Kazakstan Saint Lucia Liechtenstein Sri Lanka Liberia	LS LT LU LV MC MD MG MK ML MN MR MW MX NE NL NO NZ PL PT RO RU SD SE SG	Lesotho Lithuania Luxembourg Latvia Monaco Republic of Moldova Madagascar The former Yugoslav Republic of Macedonia Mali Mongolia Mauritania Malawi Mexico Niger Netherlands Norway New Zealand Poland Portugal Romania Russian Federation Sudan Sweden Singapore	SI SK SN SZ TD TG TJ TM TR TT UA US UZ VN YU ZW	Slovenia Slovakia Senegal Swaziland Chad Togo Tajikistan Turkmenistan Turkey Trinidad and Tobago Ukraine Uganda United States of America Uzbekistan Viet Nam Yugoslavia Zimbabwe

10

15

20

25

PREVENTION OF MARINE ENCRUSTATION ON BRONZE PROPELLERS.

This invention relates to a process for the prevention of marine encrustation on bronze propellers, which include tin bronze, aluminium bronze, silicon-aluminium bronze, nickel-aluminium bronze and manganese bronze propellers. As, in operation, water travels over the propeller blades at high velocity, it is essential for the efficiency of the propeller, that the surface be perfectly smooth, even and true. From the time that they are immersed into a marine environment, bronze propellers are prone to attack by marine organisms, such as barnacles, coral and algae, which attach themselves to the bronze metallic surface. creating lumps on the propeller, which adversely affect its balance and cause impedance and vibration of the propeller and its boat in the water. Various remedies have been tried including anti-fouling paints. One of these paints containing tributyl tin, was so toxic to other economic marine life, such as oysters, that it had to be discontinued. Its successor is so viscous, that its application to the finely polished surface of the bronze leaves brush marks in the form of grooves, which adversely affect the fine balance and vibration free performance of the propeller from day 1. Durability of the anti-fouling paint on the propeller can be as short as 30 days in active marine environments.

SUBSTITUTE SHEET (RULE 26)

Accordingly, the inventive process seeks to provide protection from marine encrustation for an extended period of time. The process for the prevention of marine encrustation on bronze surfaces, in particular those of propellers, is characterised by the following steps:-

- (a) The cast propeller is first polished to the propeller production standard.
- (b) The whole polished propeller is then cleansed, to remove all traces of dirt and grease.
- 10 (c) The cleansed propeller is then electroplated with copper to a depth of at least 0.005" or 0.15 mm.
 - (d) The electroplated propeller is then placed in a suitable container and sprayed with a standard solution of sodium hypochlorite.
- (e) The container is then sealed for at least twenty-four hours and preferably kept sealed until just prior to launching.

Thereafter, only minimum maintenance is required, when the vessel is slipped periodically, thus providing a substantial reduction in maintenance.

providing a substantial reduction in maintenance costs.

25

The first step in the preparation is polishing. Bronze propellers and associated structure are typically sand cast and require polishing to remove scale. Reference to this procedure may be found in the article " Mechanical Finishing - Polishing and Buffing ". The recommended procedure is 60# grit size at 3500 sfm for

SUBSTITUTE SHEET (RULE 26)

WO 98/07897 PCT/AU97/00543

3

roughing, followed by 180# grit size at 5500 sfm for finishing using grease as a polishing aid. The second step in the procedure consists of surface preparation or cleansing to remove all traces of dirt and grease and may consist of one or more of alkaline cleaning by dipping or electrolytic means, vapour degreasing and solvent cleaning in the article 2 m Metal Cleaning -Selection of Cleaning Process ". This surface preparation is also the subject of standard ASTM B281 - " Preparation of Copper and Copper Base Alloys for Electroplating. " The third step involves electroplating the cleansed propeller with copper to a depth of at least 0.005" or 0.15 mm. Various salts of copper may be used, but the most common are those of the two alkaline (cyanide and pyrophosphate) baths and the two acid (sulphate and fluoborate) baths. These are variously described in " Copper Plating " by Mattie F. McFadden and are the subject of two standards AMS 2418 and MIL-C-14550 (Ord). As well as providing an appropriate surface for subsequent processing, electroplating with copper enhances the surface by providing a substantial levelling effect ranging from 70 to 90 per cent for a minimum deposition of 0.005" in thickness. The fourth step in the process consists of placing the

10

15

20

25

The fourth step in the process consists of placing the electroplated propeller in a suitable container and spraying the electroplated surface with sodium hypochlorite solution. This solution is prepared by

WO 98/07897 PCT/AU97/00543

4

chlorination of sodium hydroxide (caustic soda) solution

$$2$$
NaOH + Cl_2 -> NaCl + NaClO + H_2 O

or, alternatively, by electrolysis of a sodium chloride (common salt) solution and reacting the product of the anode (chlorine) with the product of the cathode (sodium hydroxide). Sodium hypochlorite is routinely marketed as a 5% equimolecular solution of sodium chloride and sodium hypochlorite for the disinfection and sterilisation of such places as dairies and milking sheds under various trade names such as Eau de Javelle, Chlorox and Dazzle. The reactions which take place with the copper surface are believed to be

15

20

25

A first coating of black cupric oxide is formed, which coating is then converted to a blue-green basic cupric chloride. The basic cupric chloride forms a firmly adherent coating, which resists the encroachment of marine organisms. A life expectancy of five years of effective protection against marine growth has been achieved,

SUBSTITUTE SHEET (RULE 26)

5

providing ultimate thrust to manufacturers' standards, together with precise balance and vibration-free performance.

BIBLIOGRAPHY. Metals Handbook, 8th Edit., Vol.2-" Heat Treating, Cleaning and Finishing." (ASM, Metals Park, Ohio 1964). The claims defining the invention are as follow:-

1. A process for the prevention of marine encrustation on bronze surfaces, in particular those of propellers, to provide protection from marine activity for an extended period of time, characterised by the following steps:-

(a) the cast propeller is first polished to the propeller production standard:

- (b) the whole polished propeller is then cleansed, to remove all traces of dirt and grease;
- (c) the cleansed propeller is then electroplated with copper to a depth of at least 0.005" or 0.15 mm;
- 15(d) the electroplated propelle_ is then placed in a suitable container and sprayed with a standard solution of sodium hypochlorite;
- (e) the container is then sealed for at least twenty-
- A process according to Claim 1, wherein the polishing procedure is 60# grit size at 3500 sfm for roughing,

followed by 180# grit size at 5500 sfm for finishing using grease as a polishing aid.

- 3. A process according to Claim 1, wherein the surface cleansing consists of one or more of alkaline cleaning by dipping or electrolytic means, vapour degreasing and solvent cleaning.
- 4. A process according to Claim 1, wherein the copper electroplating baths are alkaline.
- 5. A process according to Claim 4, wherein the copper electroplating bath is an alkaline cyanide bath.
- 6. A process according to Claim 4, wherein the copper electroplating bath is an alkaline pyrophosphate bath.
- 7. A process according to Claim 1, wherein the copper electroplating baths are acid.
- 8. A process according to Claim 7, wherein the copper electroplating bath is an acid sulphate bath.
- 9. A process according to Claim 7, wherein the copper electroplating bath is an acid fluoborate bath.

8

10. A process according to Claim 1, wherein the container is kept sealed until just prior to launching.

International Application No. PCT/AU 97/00543

			D 97/00343
A.	CLASSIFICATION OF SUBJECT MATTER		
Int Cl6:	C23F 17/00, 15/00 B24B 1/00, C23C 22/63,	C25D 3/38, 3/40, B63H 1/14, 1/28.	
According to	International Patent Classification (IPC) or to bot	h national classification and IPC	
В.	FIELDS SEARCHED		
	umentation searched (classification system followed by a 17/00, 15/00, 7/02, B63H 1/14	classification symbols)	
	searched other than minimum documentation to the ex above, AU Cl.: 73.156.	tent that such documents are included in	the fields searched
Electronic data (See attached	base consulted during the international search (name of sheet)	f data base and, where practicable, search	terms used)
C.	DOCUMENTS CONSIDERED TO BE RELEVAN	г	
Category*	Citation of document, with indication, where ap	propriate, of the relevant passages	Relevant to claim No.
A	EP 188356 A2, (BARPRO LIMITED), 23 July line 13 and Figure 1).	1986, (see page 3 line 3 to page 5	1-10
A	GB 823531 A, (SOCIÉTÉ DE CONDENSATI MÉCANIQUES), 11 November 1959, (see pag Figures 1 to 8 of the drawings).	ION ET D'APPLICATIONS e 4 line 87 to page 6 line 82 and	1-10
X	Further documents are listed in the continuation of Box C	X See patent family ar	nnex
"A" document come internorm or when the come int	al categories of cited documents: "Inent defining the general state of the art which is insidered to be of particular relevance or document but published on or after the ational filing date ment which may throw doubts on priority claim(s) ich is cited to establish the publication date of er citation or other special reason (as specified) ment referring to an oral disclosure, use, ition or other means ment published prior to the international filing out later than the priority date claimed	priority date and not in conflict with understand the principle or theory u document of particular relevance, the be considered novel or cannot be con- inventive step when the document is document of particular relevance; the be considered to involve an inventive combined with one or more other su- combination being obvious to a pers	the application but cited to inderlying the invention is claimed invention cannot insidered to involve an is taken alone is claimed invention cannot be step when the document is inch documents, such ion skilled in the art
	ual completion of the international search	Date of mailing of the international sear	rch report
7 November 1	997.	27 NOV 1997	
	ling address of the ISA/AU I INDUSTRIAL PROPERTY ORGANISATION 2606 Facsimile No.: (02) 6285 3929	A. DAVIES Telephone No.: (02) 6283 2072	

International Application No.
PCT/AU 97/00543

C (Continua	PCT/AU 97/00543	
	TO BE RELEVANT	
Category*	Citation of document, with indication, where appropriate, of the relevant passages (Remove spaces when completed if the page is too long)	Relevant to claim No.
A	GB 1299126 A, (OYSTEIN RASMUSSEN), 6 December 1972, (see page 2 line 98 to page 3 line 47 and Figures 1 to 3 of the drawings).	1-10
A	GB 2026039 A1, (MOAT LIMITED), 30 January 1980, (see page 1 line 115 to page 3 line 38 and Figures 1 to 19 of the drawings).	1-10
A	PATENT ABSTRACTS OF JAPAN, UNEXAMINED APPLICATIONS, {CD No. 35, C25, 30, (1976-1993)}, JP 59/197590 A2, MITSUBISHI HEAVY INDUSTRIES LIMITED), 9 November 1984.	1-10
A	PATENT ABSTRACTS OF JAPAN, UNEXAMINED APPLICATIONS, {CD No. 19, B60-64 (1986-1989) (2/3)}, JP 61/012496 A2, (KAWASAKI HEAVY INDUSTRIES LTD. & TAKIRON CO. LTD.), 20 January 1986.	1-10
A	PATENT ABSTRACTS OF JAPAN, UNEXAMINED APPLICATIONS, {CD No. 108, Sep. 1994, (06/241601-06/276800)}, JP 96/270322 A2, (NIPPON STEEL CORPORATION), 27 September 1994.	1-10
A	US 3426473 A, (N.F. CARDARELLI, S.J. CAPRETTE JR.), 11 February 1969, (see page 2 line 52 to page 6 line 6 and Figures 1 to 3 of the drawings).	1-10
A	US 3458413, A, (K.UEDA, T.HORIGUCHI, M.HIRATA), 29 July 1969, (see page 2 line 63 to page 4 line 63 and Figures 1 to 3 of the drawings).	1-10
A	US 3497434 A, (E.L.LITTAUER), 24 February 1970, (see page 1 line 57 to page 3 line 17 and Figures 1 and 2 of the drawings).	1-10
A	US 5080926 A, (J.PORTER, L.SUHL), 14 January 1992, (see page 2 line 21 to page 3 line 42 and Figure 1).	1-10

International Application No.

PCT/AU 97/00543

Continuation from Box B

Search on Electronic Data Base.

DERWENT WPAT.

SS1: B63H-001/IC OR B63B-059/04/IC OR C23/IC OR C25/IC (1768)

SS2: C23C/IC OR C23D/IC OR C23F/IC OR C23G/IC OR C25D/IC OR C25F/IC (147922)

SS3: 1 OR 2 (149619)

SS4: 3 AND BRONZE (556)

SS5: 3 AND BRONZ: (572)

SS6: 5 AND (NEPTUN: OR MARINE OR MARITIME OR AQUATIC OR SEA OR OCEAN OR SUBMARINE OR UNDERWATER OR SUBAQU: OR SEA (W) WATER OR UNDERSEA) (9)

SS7: C23F-015/00/IC OR C23F-017/00/IC (3155)

SS8: 7 AND (ELECTROPLAT: OR PLAT: OR COPPER: OR CU) (872)

SS9: 5 AND (ELECTROPLAT: OR PLAT: OR COPPER: OR CU) (401)

SS10: 8 AND BRONZ: (14)

SS11: 9 AND (NEPTUN: OR MARINE OR MARITIME OR AQUATIC OR SEA OR OCEAN OR SUBMARINE OR UNDERWATER OR SUBAQU: OR SEA (W) WATER OR UNDERSEA) (4)

SS12: 6 OR 10 OR 11 (23)

SS13: 12 AND 75-95 (20)

(PRE- AND POST- 75-95 PRINTED SEPARATELY)

JAPIO.

SS1: B63H-001/IC OR B63B-059/04/IC OR C23/IC OR C25/IC (712)

SS2: C23C/IC OR C23D/IC OR C23F/IC OR C23G/IC OR C25D/IC OR C25F/IC (92435)

SS3: 1 OR 2 (93114)

SS4: 3 AND BRONZE (151)

SS5: 3 AND BRONZ: (154)

SS6: 5 AND (NEPTUN: OR MARINE OR MARITIME OR AQUATIC OR SEA OR OCEAN OR SUBMARINE OR UNDERWATER OR SUBAQU: OR SEA (W) WATER OR UNDERSEA) (6)

SS7: C23F-015/00/IC OR C23F-017/00/IC (1008)

SS8: 7 AND (ELECTROPLAT: OR PLAT: OR COPPER: OR CU) (298)

SS9: 5 AND (ELECTROPLAT: OR PLAT: OR COPPER: OR CU) (114)

SS10: 8 AND BRONZ: (1)

SS11: 9 AND (NEPTUN: OR MARINE OR MARITIME OR AQUATIC OR SEA OR OCEAN OR SUBMARINE OR UNDERWATER OR SUBAQU: OR SEA (W) WATER OR UNDERSEA) (4)

SS12: 6 OR 10 OR 11 (7)

(7 ABSTRACTS PRINTED)

Information on patent family members

International Application No. PCT/AU 97/00543

This Annex lists the known "A" publication level patent family members relating to the patent documents cited in the above-mentioned international search report. The Australian Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

	iais which are mere	ly given for	r the purpose of in	formation	.		
Patent 1	Document Cited in Sea Report	arch		Pat	ent Family Member		
EP	188356 A2	AU US	52410/86 A1 4724107 A	JP	61/217250 A2	NO	860123 A
GB	823531 A	NOT	KNOWN				
GB	1299126 A	NOT	KNOWN				
GB	2026039 A1	AU NO	49154/79 A1 792426 A	DK WO	1066/80 A 80/00262 A1	EP	16080 A1
JP	59/197590 A2	NONE					
JP	61/012496 A2	NONE					
JP	06/270322 A2	NONE					
US	3426473 A	DE	1621935 A	ES	338679 A1	FR	1521867 A5
		GB	1185902 A	NL	6704657 A	SE	344313 B
US	3458413 A	DE	1642486 A	FR	1474268 A5	NL	6602891 A
US	3497434 A	DE	1771835 A	FR	1576662 A	GB	1176274 A
		JP	48/039343 A2	NL	6810165 A	SE	347924 B
US	5080926 A	NONE					
							END OF ANNE